

SPC FLOORING TILE TECHNICAL DATA

Sizes		1220x310 mm
Total thickness		6,0mm
SPC core		4,5 mm
Padding		1,5 mm EVA
N.W.		9.5 KG/m ²
Bevel		V-bevel 4 sides
Colour fastness to light	EN ISO105 B02:2014	6
Dimensional stability	ISO23999:2012	0,10 %
Expansion in temperature change from 23 °C-45 °C		0,010 %
Shrinkage in temperature change from 23 °C-5°C		0,047 %
Urling after heat exposure	ISO23999:2012	0 mm
Fire behavior.	UNE-EN 13823:2012	B-s1,d0
Formaldehyde emissions	EN717-1:2004	PASS
Swelling in thickness after immersion in water	EN317:1994	0,9 %
Determination of residual indentation	EN ISO24343-1:2012	0,04 mm
VOC emissions testing	ISO:16000/3,6,9,11	A+
VOC emissions testing CDPH1350	California Specification01350	PASS
JS California Proposition 65 - Phthalate		PASS

SPC FLOORING TILE TECHNICAL DATA

Sizes		620x310 mm
Total thickness		6,0mm
SPC core		4,5 mm
Padding		1,5 mm EVA
N.W.		9.5 KG/m ²
Bevel		V-bevel 4 sides
Colour fastness to light	EN ISO105 B02:2014	6
Dimensional stability	ISO23999:2012	0,10 %
Expansion in temperature change from 23 °C-45 °C		0,010 %
Shrinkage in temperature change from 23 °C-5°C		0,047 %
Urling after heat exposure	ISO23999:2012	0 mm
Fire behavior.	UNE-EN 13823:2012	B-s1,d0
Formaldehyde emissions	EN717-1:2004	PASS
Swelling in thickness after immersion in water	EN317:1994	0,9 %
Determination of residual indentation	EN ISO24343-1:2012	0,04 mm
VOC emissions testing	ISO:16000/3,6,9,11	A+
VOC emissions testing CDPH1350	California Specification01350	PASS
JS California Proposition 65 - Phthalate		PASS

SPC WALL PANEL TILE TECHNICAL DATA

Sizes		800x400 mm
Total thickness		4,0mm
N.W.		8.45 KG/m ²
Bevel		V-bevel 4 sides & Painted
Colour fastness to light	EN ISO105 B02:2014	6
Dimensional stability	ISO23999:2012	0,10 %
Expansion in temperature change from 23 °C-45 °C		0,010 %
Shrinkage in temperature change from 23 °C-5°C		0,047 %
Urling after heat exposure	ISO23999:2012	0 mm
Fire behavior.	UNE-EN 13823:2012	B-s1,d0
Formaldehyde emissions	EN717-1:2004	PASS
Swelling in thickness after immersion in water	EN317:1994	0,9 %
Determination of residual indentation	EN ISO24343-1:2012	0,04 mm
VOC emissions testing	ISO:16000/3,6,9,11	A+
VOC emissions testing CDPH1350	California Specification01350	PASS
JS California Proposition 65 - Phthalate		PASS